

Observation of superconductivity in Y_2PdGe_3 , structurally same as MgB_2

E.V. Sampathkumaran[†] and Subham Majumdar

Tata Institute of Fundamental Research, Homi Bhabha Road, Colaba, Mumbai-400005, India

The results of electrical resistance (1.4 - 300 K), magnetization (2-300 K) and heat-capacity (2 - 50 K) measurements in Y_2PdGe_3 , found to crystallize in a AlB_2 -derived hexagonal structure, are reported¹. The results establish that this compound is superconducting below 3 K. This observation is interesting considering that this compound is the first superconductor among the ternary members derived from the hexagonal AlB_2 structure. With superconductivity being *uncommon even among binary alloys derived from AlB_2 structure* and with recent excitement on the observation of high temperature superconductivity in MgB_2 , this finding gains importance.

Recent observation [1] of superconductivity with T_c close to 40 K in MgB_2 has caused considerable excitement among condensed matter physicists. [2,3] This compound crystallizes in the hexagonal AlB_2 -type structure, which is made up of alternating of hexagonal layers of Al and graphite-like honeycomb layers of B atoms. This observation of superconductivity is further fascinating, particularly when one notes that this structure is generally unfavorable for superconductivity. Thus, for instance, among the rare-earth disilides and germanides having the same electron concentration (YSi_2 , YGe_2 , LaSi_2 and LaGe_2), only those with the α - ThSi_2 structure (YGe_2 , LaSi_2 and LaGe_2 , structurally slightly different from that of AlB_2) have been found to be superconducting; [4-6] even for ThSi_2 , the α -tetragonal form exhibits a higher T_c (3.16 K) than the β -form which is of AlB_2 -type (2.4 K). [7,8] Thus, it is of interest to search for superconductors among compounds crystallizing in the AlB_2 -type structure, particularly to look for the ones not containing B in view of a proposal that B, being a light atom, plays a vital role to favor superconductivity in this structure.

During last few years, we have been actively involved in synthesizing new compounds of the type R_2XY_3 , with crystal structures derived from that of AlB_2 (Ref. 9). Though we noticed several interesting magnetic anomalies, [10-20] in particular relevant to the fields of Kondo

lattices and heavy-fermions, non-Fermi-liquids, colossal magnetoresistance, magnetic refrigeration and possibly low-dimensional magnetism, it is to be noted that none of the present family of compounds has been found (or earlier reported) to be superconducting. Here, we report the formation of the compound, Y_2PdGe_3 , in the AlB_2 -derived structure and find it to be the first superconductor among this family of ternary compounds (that is, with 2:1:3 stoichiometry) with a superconducting transition temperature (T_c) of 3 K.

The samples were prepared by arc melting stoichiometric amounts of constituent elements in an inert atmosphere. The ingots were homogenised in an evacuated, sealed quartz tube at 850 C. X-ray diffraction patterns were obtained employing $\text{Cu K}\alpha$ radiation and the patterns confirm that the compounds crystallize in an AlB_2 -derived hexagonal structure. There is an additional weak line (about 5%), which we believe is due to a parasitic phase with the stoichiometry 1:2:2. We do not find any superstructure line in the X-ray diffraction patterns within the detection limit and hence we believe that there is no doubling of unit-cell parameters ($a = 4.192 \text{ \AA}$ and $c = 4.000 \text{ \AA}$) unlike in some other isostructural compounds. [1,20] The electrical resistivity (ρ) measurements ($T = 1.4\text{-}300 \text{ K}$) were performed by a conventional four-probe method employing a silver paint for making electrical contacts. The field-cooled (FC) and the zero-field-cooled (ZFC) magnetic susceptibility (χ) behavior ($H = 25 \text{ Oe}$) below 10 K, and the heat-capacity (C) data (2.5-30 K) by semi-adiabatic heat-pulse method were also obtained.

With respect to the high temperature ρ behavior, there is a normal metallic behavior of ρ with the variation of T . However, at 3 K, there is a sharp drop of ρ (Fig. 1) to zero (within the accuracy of nanovoltmeter employed to measure the voltage drop across the leads) as T is lowered, as if this compound is superconducting below ($T_c =$) 3 K. To support this finding, the χ has also been measured at low fields (25 Oe) and we find that there is an onset of strong diamagnetism below 3 K and the divergence of ZFC and FC χ is typical of that expected for type-II superconductors. A comparison of the magnitude of the value of ZFC- χ at 2 K with that of other known

¹The report of superconductivity in Y_2PdGe_3 has been communicated by us to Physical Review B about few months back

standard superconductors like Pb establishes bulk nature of superconductivity. The plot of M versus H (see Fig. 1, inset) at 1.7 K is typical of that of type-II superconductors with a value of lower critical field of about 400 Oe. In order to render further support to the bulk nature of superconductivity, C was also measured down to 2.5 K and the upturn observed in the data obtained below 3 K (see Fig. 1, bottom inset) is sufficient to establish bulk superconductivity; the broadened signal around the transition could possibly due to inhomogeneities. The values of the Debye temperature and the electronic term (γ) inferred from the data in the range 5 - 15 K turn to be about 130 K and 2.5 mJ/mol K² respectively. If one employs this value of γ , the value of $\Delta C/\gamma T_c$ turns to be close to 3, which is far away from the weak coupling value of 1.35.

To conclude, we report the formation of a new compound, Y₂PdGe₃, in the hexagonal AlB₂-structure and studied its physical characteristics. This compound has been identified to be the lone superconductor till date in this family of ternary rare-earth compounds. We hope that the observation of superconductivity in a AlB₂-type compound, not containing B, may be helpful for overall theoretical understanding of high T_c in MgB₂. Finally we would like to state that a weak superconducting signal around 7 K has been obtained even in the composition Y₂PdSi₃ [21].

† *E-mail address: sampath@tifr.res.in*

[1] J. Akimitsu, Symposium on Transition Metal Oxides, Sendai, January 10, 2001.
[2] J. Kortus, H. Mazin, K.D. Belashchenko, V.P. Antropov and L.L. Boyer, cond-mat/0101446.
[3] S.L. Budko, G. Lapertot, C. Petrovic, C.E. Cunningham, N. anderson and P.C. Canfield, cond-mat/0101463.
[4] B.T. Matthias, E. Corenzwet and W. Zachariasen, Phys. Rev. **112**, 89 (1958).
[5] I. Mayer, E. Yanir and I. Shidlovsky, Inorg. Chem. **6**, 842 (1968).
[6] W.E. Henry, C. Betz and H. Muir, Bull. Am. Phys. Soc., **7**, 474 (1962) and **7**, 621 (1962).
[7] G.F. Hardy and J.K. Hulm, Phys. Rev. **93**, 1004 (1953).
[8] A.S. Cooper, E. Corenzwit, L.D. Longinotti, B.T. Matthias and W.H. Zachariasen, **67**, 313 (1970).
[9] P.A. Kotsanidis, J.K. Yakinthos and E. Gamari-Seale, J. Magn. Magn. Mater. **87**, 199 (1990); B. Chevalier,

P. Lejay, J. Etourneau, and P. Hagenmuller, Solid State Commun. **49**, 753 (1984); R.A. Gordon, C.J. Warren, M.G. Alexander, F.J. Di Salvo and R. Pöttgen, J. Alloys and Compounds, **248**, 24 (1997).
[10] R. Mallik, E.V. Sampathkumaran, M. Strecker and G. Wortmann, Europhys. Lett. **41**, 315 (1998).
[11] Subham Majumdar and E.V. Sampathkumaran, Phys. Rev. B **61**, 43 (2000).
[12] Subham Majumdar, M. Mahesh Kumar, R. Mallik and E.V. Sampathkumaran, Solid State Commun. **110**, 509 (1999).
[13] Subham Majumdar, R. Mallik, E.V. Sampathkumaran, K. Rupprecht and G. Wortmann, Phys. Rev. B **60**, 6770 (1999); R. Mallik, E.V. Sampathkumaran and P.L. Paulose, Solid State Commun. **106**, 169 (1998).
[14] E.V. Sampathkumaran, I. Das, R. Rawat and Subham Majumdar, Appl. Phys. Lett. **77**, 418 (2000).
[15] R. Mallik, E.V. Sampathkumaran, M. Strecker, G. Wortmann, P.L. Paulose and Y. Ueda, J. Magn. Magn. Mater. **185**, L135 (1998).
[16] Subham Majumdar, E.V. Sampathkumaran, P.L. Paulose, H. Bitterlich, W. Löser and G. Behr have communicated an article for publication on the magnetic anomalies in single crystalline Tb₂PdSi₃.
[17] S.R. Saha, H. Sugawara, T.D. Matsuda, H. Sato, R. Mallik and E.V. Sampathkumaran, Phys. Rev. B **60**, 12162 (1999).
[18] S.R. Saha, H. Sugawara, T.D. Matsuda, Y. Aoki, H. Sato and E.V. Sampathkumaran, Phys. Rev. B **62**, 425 (2000).
[19] Subham Majumdar, M. Mahesh Kumar and E.V. Sampathkumaran, J. Alloys and Comp. **288**, 61 (1999).
[20] R. Mallik, E.V. Sampathkumaran, P.L. Paulose, H. Sugawara and H. Sato, Pramana-J.Phys. **51**, 505 (1998), Subham Majumdar, E.V. Sampathkumaran, D. Eckert, A. Handstein, K.-H. Mueller, S.R. Saha, H. Sugawara and H. Sato, J. Phys.: Cond. Matter. **28**, L337 (1999); Subham Majumdar, R. Mallik, E.V. Sampathkumaran, P.L. Paulose and K.V. Gopalakrishnan, Phys. Rev. B **59**, 4244 (1999); A. Szytula, M. Hofmann, B. Penc, M. Slaski, Subham Majumdar, E.V. Sampathkumaran and A. Zygmunt, J. Magn. Magn. Mater. **202**, 365 (1999); Subham Majumdar and E.V. Sampathkumaran, Phys. Rev. B, **62**, 8959 (2000).
[21] R. Mallik and E. V. Sampathkumaran, J. Magn. Magn. Mater. **164**, L13 (1996)

FIG. 1. Electrical resistivity and magnetic susceptibility ($H=25$ Oe) behavior at low temperatures for Y₂PdGe₃ to highlight the features due to superconducting transition. The top inset shows the field dependence of M at 1.7 K for increasing and then decreasing field for the ZFC state of the specimen and the bottom inset shows the plot of heat capacity versus temperature to highlight the feature around superconducting transition. The line through the ρ data serves as a guide to the eyes.

